

10/566 000

IAP9 Rec'd PCT/PTO 27 JAN 2006


THE FOLLOWING IS THE ENGLISH TRANSLATION OF THE
AMENDMENTS TO THE INTERNATIONAL PRELIMINARY
EXAMINATION UNDER ARTICLE 34:
Amended Sheets (page 12)

Annex to letter to EPO Munich dated 23.05.2005 concerning International Patent Application No. PCT/EP2004/003868 in the name of Röhm GmbH & Co. KG (Our Reference: OZ 2180)

5

Patent claims

1. The use of the compound



- 10 as release agent during the cast polymerization of methyl methacrylate mixtures, where:

15 R^1 = methyl, ethyl, propyl, isopropyl, butyl, isobutyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl

R^2 = methyl, ethyl, propyl, isopropyl, butyl

n = 1 or 2

m = 2 or 1 and $n + m = 3$

- 20 2. The use of the compound of the formula I in amounts of 0.01 - 5% by weight, based on the weight of the polymerizable monomers or monomer mixture composed of (meth)acrylates and of other, copolymerizable monomers, as release agent.

25

3. The use of the release agents as claimed in claim 1 or 2 for production of plastics moldings composed of (meth)acrylates and of other copolymerizable monomers.

30

4. A plastics molding composed of (meth)acrylates and of other copolymerizable monomers, comprising compounds of the formula I.